


NUTS


NYLON INSERT (ELASTIC) STOP











Grade-8

NYLON INSERT STOP NUTS, LIGHT HEX, GRADES 5 & 8 Esna®								
			F		н		G	
Nominal Size or Basic Thread Diameter		Width Across Flats		Thickness		Side Height	Width Across Corners	
		Мах	Min	Max	Min	Ref	Ref	
1/4	0.2500	.439	.430	.328	.298	.225	.482	
5/16	0.3125	.502	.492	.359	.329	.250	.552	
3/8	0.3750	.564	.553	.468	.438	.335	.622	
7/16	0.4375	.627	.616	.468	.438	.324	.694	
1/2	0.5000	.752	.741	.609	.579	.464	.837	
9/16	0.5625	.877	.865	.656	.626	.469	.978	
5/8	0.6250	.940	.928	.765	.735	.593	1.051	
3/4	0.7500	1.064	1.052	.890	.860	.742	1.191	
7/8	0.8750	1.252	1.239	.999	.969	.790	1.403	
1	1.0000	1.440	1.427	1.078	1.016	.825	1.615	
1-1/8	1.1250	1.627	1.614	1.203	1.141	.930	1.826	
1-1/4	1.2500	1.814	1.801	1.422	1.360	1.125	2.038	
1-3/8	1.3750	2.008	1.973	1.609	1.547	1.282	2.232	
1-1/2	1.5000	2.197	2.159	1.640	1.578	1.313	2.416	

Description	Heat treated hex nut with a nylon-filled collar at its back end. The grade-5 nut shall be marked with a dot and dash on the chamfered surface of the nut, 120° apart. The grade-8 nut shall be grade-marked in one of two ways: (1) with double notched corners or (2) with six symmetrically spaced identical symbols on the chamfered surface on top of the nut. When the cap-screw or bolt reaches the collar, the threads and nylon form a tight, frictional fit, restricting movement of the cap-screw or bolt when it is subjected to vibration. The nylon insert comes in various colors.					
Applications/ Advantages	Designed to be used in structural applications with Grade-5 cap-screws or bolts which have a minimum tensile strength of 120,000 psi Nylon insert nuts are not designed to be used at temperatures over 250° F. Designed to be used in structural applications with Grade-8 ca or bolts which have a minimum tensile strength of 150,000 psi. Some such applications include engines, turbines, hydraulic railroads and aerospace. Nylon insert nuts are not designed to temperatures over 250° F.					
Material	Shall be made from a low carbon steel that conforms to the following chemical composition: <i>Carbon</i> : 0.55% max.; <i>Manganese</i> : 0.30% min.; <i>Phosphorous</i> : 0.05% max.; <i>Sulfur</i> : 0.05% max.	Heat treated AISI C1137 or equivalent steel.				
Hardness	Rockwell C28 max.	Rockwell C 26 - 34				
Proof Load	120,000 psi.	150,000 psi.				
Plating	Grade-5 nylon insert stop nuts are usually supplied zinc-plated.	Grade-8 nylon insert stop nuts are usually supplied zinc yellow-plated. See Appendix-A for more information.				

Esna® is a registered trademark of the MacLean-Fogg Company. Our stop nuts are not manufactured by or connected with the producers of Esna® nuts.